



## PRODUCT INFORMATION

### SENOSON® C60 EG

#### Characteristics

Multilayer composite made of PC-ABS blend carrier layer with toughness and high heat resistance. Equipped with and easyglide® base layer

#### Advantages

- ductile breaking behaviour (no shiver)
- good directional stability
- good recyclability
- chemical resistance
- high impact strength

#### Technical properties

Property	Value
Density	1.12 g/cm <sup>3</sup>
E-Modul	2250 MPa
Vicat B/50	120°C (ISO 306)
HDT 1,82 MPa	110°C (ISO 75)
Burning behaviour	UL94 HB

#### Product details

CO-EX **senosan® C60EG**  
regrind possible

Thickness: 2.0 to 8.0 mm  
Width: up to 2200 mm  
(special formats on request)

Surface: smooth/embossed  
Colour: on request  
Embossings: 006RR; 012RN, 003FN

#### Min. quantity 3t

per thickness: 1t  
per colour: 3t  
per embossing: 3t

Price on request; smaller quantities only possible in co-production.

#### Possible applications

e.g. automotive and transport external and internal applications. UV stabilized possible and paint after applications.

Plastic Materials and Processes (NZ) Ltd  
13 John Glenn Avenue  
Albany 0632  
PO BOX 300 - 703  
Albany 0752  
New Zealand

Phone +64 9 414 1600  
Fax +64 9 415 0069  
info@pmpnewzealand.co.nz



Plastic Materials and Processes (Australia) Pty Ltd  
13 Goodyear Drive  
Thomastown,  
Victoria 3074,  
Australia

Phone +61 3 9464 4822  
Fax +61 3 9464 4677  
sales@pmpaustralia.com.au