



PRODUCT INFORMATION

SENOSON® C60FR-3

Characteristics

ABS/PC compound with flame retardant properties.

Advantages

- flame retardant
- anti-drip behaviour
- matt appearance
- ductile breaking behaviour (no shiver)
- good recyclability
- chemical resistance
- good insulation properties

Technical properties

Property	Value
Density	1.30 g/cm ³
E-Modul	3600 MPa
Vicat B/50	110 °C (ISO 306)
HDT 1,82 MPa	94 °C (ISO 75)
Burning behaviour	UL94 V-0 (from 0,8 mm)
Burning behaviour	ECE-R 118 (app. 6, 7, 8)
CLTE	6x10 ⁻⁵ k ⁻¹

Product details

CO-EX **senosan® C60FR-3**
regrind possible

Thickness: 2.0 to 6.0 mm
Width: up to 2200 mm
(special formats on request)
Surface: smooth/embossed
Colour: on request
Embossings: 006RR; 012RN

Min. quantity 5t

per thickness: 1t
per colour: 3t
per embossing: 3t

Price on request; smaller quantities only possible in co-production.

Possible applications

Ceiling and side panels in busses.